

Flame Retardant ABS POLYLAC® PA-764

產品敘述: F.R. Weather resistant

物性	ISO 測試方法	測試條件	單位	PA-764
熔融指數	1133	220°C×10KG	ml/10 min	28
比重	1183	23 °C	g/cm ³	1.19
拉伸強度	527	50 mm/min, yield	MPa	36
		50 mm/min, break	MPa	27
延伸率	527	50 mm/min	%	10
彎曲強度	178	2 mm/min	MPa	55
彎曲彈性模數		2 mm/min	GPa	1.7
IZOD 衝擊強度	180/1A	23 °C Notched	KJ/m ²	13
		-30 °C Notched	KJ/m ²	7
Charpy 衝擊強度	179	23 °C Notched	KJ/m ²	13
		-30 °C Notched	KJ/m ²	7
維氏軟化溫度	306	1 Kg,50 °C/hr	°C	101
		5 Kg,50 °C/hr	°C	90
熱變形溫度	75/A	1.8 MPa Unannealed	°C	82
		1.8 MPa Annealed	°C	92
線膨脹係數	11359	-	-	8.46 x 10 ⁻⁵
燃燒等級	-	UL-94	-	1.5mm V-0 1.5mm 5VB 2.5mm 5VA
成型收縮率	294-4	-	%	0.3~0.6
標記	1043	-	-	>ABS-FR(17)<

April 26, 2019

Notes : These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

The above statement is based on our current level of knowledge and covers the above products directly manufactured and supplied by CHI MEI CORPORATION at the date of issue. CHI MEI CORPORATION makes no warranties, whether express or implied, and assumes no liability in connection with any use of above information. Notwithstanding the foregoing, CHI MEI CORPORATION shall in no event be held obligated or liable for any claims due to or arising from (i) any customer provided, consigned, materials and/or parts, which are incorporated or adopted in the products; (ii) any combination of the products with material not provided or authorized by our company; (iii) any modifications to the products which are made or directed by customer; (iv) our compliance with the specifications, instructions, and/or designs provided by customer; (v) any anti-trust, unfair competition and/or other unlawful actions effected by customer; or (vi) any defects, infringement, breach and/or violation which are arising out of customer's faults or otherwise not solely and directly attributable to CHI MEI CORPORATION. In no event will CHI MEI CORPORATION be liable for any indirect, special, exemplary, punitive, or consequential damages (including lost profits) of any nature whatsoever whether arising out of the purchase, shipment, unloading, handling, or use of any product or otherwise.