

Vydyne® 47 NT

polyamide 66



Vydyne 47 NT is a general-purpose, impact-modified PA66 resin. Available in natural, Vydyne 47 NT is recognized for all the processing and property advantages inherent to PA66 with the addition of improved impact strength. This resin offers a well balanced combination of engineering properties characterized by

high melt point, good surface lubricity, abrasion resistance and resistance to many chemicals, machine and motor oils, solvents and gasoline. Vydyne 47 NT is designed to meet the critical low-temperature impact requirements called out in many automotive specifications.

General				
Material Status	• Commercial: Active			
Availability	• Asia Pacific	• Europe	• North America	
Additive	• Impact Modifier			
Features	• Abrasion Resistant • Chemical Resistant • Gasoline Resistant • General Purpose	• Good Processability • Good Toughness • High Impact Resistance • Impact Modified	• Low Temperature Impact Resistance • Low Temperature Toughness • Oil Resistant • Solvent Resistant	
Uses	• Automotive Applications • Connectors • Consumer Applications	• Electrical/Electronic Applications • Fasteners • Gears	• Industrial Applications	
Agency Ratings	• ASTM D4066 PA0151	• ASTM D6779 PA0151		
Appearance	• Natural Color			
Forms	• Pellets			
Processing Method	• Injection Molding			

Physical	Dry	Conditioned	Unit	Test Method
Density	1.10	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.6	--	%	
Flow : 23°C, 2.00 mm	1.8	--	%	
Water Absorption				ISO 62
24 hr, 23°C	1.2	--	%	
Equilibrium, 23°C, 50% RH	2.3	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	2780	1740	MPa	ISO 527-2
Tensile Stress				ISO 527-2
Yield, 23°C	60.0	45.0	MPa	
Break, 23°C	52.0	40.0	MPa	
Tensile Strain (Break, 23°C)	22	60	%	ISO 527-2
Flexural Modulus (23°C)	2300	780	MPa	ISO 178
Flexural Stress (23°C)	70.0	24.0	MPa	ISO 178

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-40°C	11	18	kJ/m ²	
-30°C	17	24	kJ/m ²	
23°C	19	62	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179
-30°C	No Break	No Break		
23°C	No Break	No Break		
Notched Izod Impact Strength				ISO 180
-40°C	12	18	kJ/m ²	
-30°C	16	24	kJ/m ²	
23°C	18	44	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	185	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	63.0	--	°C	ISO 75-2/A
Melting Temperature	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	1.1E-4	--	cm/cm/°C	
Transverse : 23 to 55°C, 2.00 mm	1.4E-4	--	cm/cm/°C	
RTI Elec				UL 746
0.75 mm	125	--	°C	
1.5 mm	125	--	°C	
3.0 mm	125	--	°C	
RTI Imp				UL 746
0.75 mm	75.0	--	°C	
1.5 mm	75.0	--	°C	
3.0 mm	75.0	--	°C	
RTI Str				UL 746
0.75 mm	85.0	--	°C	
1.5 mm	85.0	--	°C	
3.0 mm	85.0	--	°C	

Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.750 mm)	1.0E+12	--	ohms-cm	IEC 60093
Dielectric Strength (1.00 mm)	24	--	kV/mm	IEC 60243
Arc Resistance	PLC 5	--		ASTM D495
Comparative Tracking Index (3.00 mm)	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.75 mm	PLC 0	--		
1.5 mm	PLC 0	--		
3.0 mm	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 1	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.75 mm	PLC 4	--		
1.5 mm	PLC 4	--		
3.0 mm	PLC 2	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.75 mm	HB	--		
1.5 mm	HB	--		
3.0 mm	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.75 mm	750	--	°C	
1.5 mm	775	--	°C	
3.0 mm	725	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.75 mm	775	--	°C	
1.5 mm	800	--	°C	
3.0 mm	750	--	°C	
Additional Information	Dry	Conditioned	Unit	Test Method
Automotive Materials - (thickness d = 1 mm)	+	--		FMVSS 302

Injection	Dry Unit
Drying Temperature	80 °C
Drying Time	4.0 hr
Suggested Max Regrind	25 %
Rear Temperature	280 to 310 °C
Middle Temperature	280 to 310 °C
Front Temperature	280 to 310 °C
Nozzle Temperature	280 to 310 °C
Processing (Melt) Temp	285 to 305 °C
Mold Temperature	65 to 95 °C

Notes

Typical properties: these are not to be construed as specifications.

¹ Typical properties: these are not to be construed as specifications.



North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 2315 0888

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.