

Amodel® A-1133 HS

polyphthalamide

Amodel® A-1133 HS is a 33% glass reinforced, heat stabilized polyphthalamide (PPA) with a high heat deflection temperature, high flexural modulus and high tensile strength. Excellent creep resistance and low moisture absorption are also characteristic of this resin. Testing conducted on samples dry as molded and samples

conditioned to 50% relative humidity in accordance with ISO-1110, Accelerated Method.

- Black: A-1133 HS BK 324
- Natural: A-1133 HS NT

General

Material Status	<ul style="list-style-type: none"> • Commercial: Active 	
Availability	<ul style="list-style-type: none"> • Africa & Middle East • Asia Pacific • Europe 	<ul style="list-style-type: none"> • Latin America • North America
Filler / Reinforcement	<ul style="list-style-type: none"> • Glass Fiber, 33% Filler by Weight 	
Additive	<ul style="list-style-type: none"> • Heat Stabilizer 	
Features	<ul style="list-style-type: none"> • Chemical Resistant • Creep Resistant • Good Dimensional Stability • Good Stiffness • High Heat Resistance 	<ul style="list-style-type: none"> • High Stiffness • High Strength • High Temperature Strength • Low Moisture Absorption
Uses	<ul style="list-style-type: none"> • Automotive Applications • Automotive Electronics • Automotive Interior Parts • Automotive Under the Hood • Cell Phones • Connectors • Fuel Lines 	<ul style="list-style-type: none"> • Housings • Industrial Applications • Industrial Parts • Machine/Mechanical Parts • Metal Replacement • Power/Other Tools
RoHS Compliance	<ul style="list-style-type: none"> • RoHS Compliant 	

Amodel® A-1133 HS

polyphthalamide

General

	<ul style="list-style-type: none"> • 3M 11-0003-5762-1 Color: Colors • 3M 11-0003-5762-1 X62 4200 • ASTM D4000 PA121 G35 Color: BK324 Black • ASTM D4000 PA121 G35 Color: NT Natural • ASTM D6779 PA121G35 • BOSCH N28 BN05-OX1 BN0510-GF35-0Anf01SO Color: NT Natural • BOSCH N28 BN05-OX1 BN0510-GF35-0Asw01SO Color: BK-324 Black • CHRYSLER MS-DB-478 CPN4242 Color: NT Natural • CHRYSLER MS-DB-478 Type A CPN3598 Color: BK324 Black • DELPHI M-53290 Color: BK324 Black • DELPHI M-53290 Color: NT Natural • DELPHI M-6071 Color: NT Natural • DELPHI MS-5216 Color: BK324 Black • DELPHI MS-5216 Color: NT Natural • FORD WSP-M4D843-A Color: BK324 Black • FORD WSP-M4D843-A Color: NT Natural • GM GMP.PPA.004 Color: BK324 Black • GM GMP.PPA.004 Color: NT Natural • GM GMW15702-110020 >PPA+GF33< (A4, A22, A64, BA633, DC1473, G20, KM1158, KS2300, LS20, RS9, SS260, Z1) Color: NT Natural ¹ • GM GMW16356P-PPA-GF35 Color: BK-324 Black • GM GMW16356P-PPA-GF35 Color: NT Natural • IMDS ID 21195756 Color: Black • IMDS ID 21195756 Color: Natural • PSA Peugeot-Citroën SPA X62 4200 • TRW S-13318701 Color: BK543 Black • VALEO VMS-4470 Color: BK324 Black • VALEO VMS-4470 Color: NT Natural • YAZAKI YPES-25-02-135 Color: NT Natural
Automotive Specifications	
UL File NumberGlobal	• E95746
Appearance	• Black • Natural Color
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PA6T/6I/66-GF33<

Physical	Dry	Conditioned	Unit	Test method
Density	1.48	--	g/cm ³	ISO 1183/A
Molding Shrinkage				ASTM D955
Flow	0.40	--	%	
Across Flow	0.80	--	%	
Water Absorption (24 hr)	0.23	--	%	ASTM D570

Mechanical	Dry	Conditioned	Unit	Test method
Tensile Modulus				
--	13100	13100	MPa	ASTM D638
23°C	13400	--	MPa	ISO 527-2
100°C	10800	--	MPa	ISO 527-2
150°C	6700	--	MPa	ISO 527-2
175°C	4300	--	MPa	ISO 527-2

Amodel® A-1133 HS

polyphthalamide

Mechanical	Dry	Conditioned	Unit	Test method
Tensile Stress				
Break, 23°C	233	--	MPa	ISO 527-2
Break, 100°C	148	--	MPa	ISO 527-2
Break, 150°C	80.0	--	MPa	ISO 527-2
Break, 175°C	72.0	--	MPa	ISO 527-2
--	221	193	MPa	ASTM D638
Tensile Elongation				
Break	2.5	2.1	%	ASTM D638
Break, 23°C	2.5	--	%	ISO 527-2
Break, 100°C	2.9	--	%	ISO 527-2
Break, 150°C	8.7	--	%	ISO 527-2
Break, 175°C	8.5	--	%	ISO 527-2
Flexural Modulus				
--	11400	11400	MPa	ASTM D790
23°C	11600	--	MPa	ISO 178
100°C	9800	--	MPa	ISO 178
150°C	4000	--	MPa	ISO 178
175°C	3600	--	MPa	ISO 178
Flexural Strength				
--	317	254	MPa	ASTM D790
23°C	319	--	MPa	ISO 178
100°C	227	--	MPa	ISO 178
150°C	93.0	--	MPa	ISO 178
175°C	80.0	--	MPa	ISO 178
Compressive Strength				
	185	--	MPa	ASTM D695
Shear Strength				
	101	88.9	MPa	ASTM D732
Poisson's Ratio				
	0.41	--		ASTM E132
Impact				
Charpy Notched Impact Strength (23°C)				
	9.5	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)				
	73	--	kJ/m ²	ISO 179/1eU
Notched Izod Impact				
--	80	59	J/m	ASTM D256
23°C	8.8	--	kJ/m ²	ISO 180/1A
Unnotched Izod Impact				
--	770	--	J/m	ASTM D256
23°C	49	--	kJ/m ²	ISO 180/1U
Hardness				
Rockwell Hardness (R-Scale)				
	125	--		ASTM D785
Thermal				
Deflection Temperature Under Load				
0.45 MPa, Annealed, 3.20 mm	297	--	°C	ASTM D648
1.8 MPa, Unannealed	280	--	°C	ISO 75-2/A
1.8 MPa, Annealed, 3.20 mm	285	--	°C	ASTM D648

Amodel® A-1133 HS

polyphthalamide

Thermal	Dry	Conditioned	Unit	Test method
Continuous Use Temperature				ASTM D3045
-- ²	164	--	°C	
-- ³	185	--	°C	
Melting Temperature	313	--	°C	ASTM D570 ISO 11357-3
CLTE				ASTM E831
Flow : 0 to 100°C	2.4E-5	--	cm/cm/°C	
Flow : 100 to 200°C	2.7E-5	--	cm/cm/°C	
Transverse : 0 to 100°C	5.5E-5	--	cm/cm/°C	
Transverse : 100 to 200°C	1.1E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test method
Volume Resistivity	1.0E+16	2.0E+15	ohms·cm	ASTM D257
Dielectric Strength (3.20 mm)	21	21	kV/mm	ASTM D149
Dielectric Constant				ASTM D150
60 Hz	4.40	4.70		
1 MHz	4.20	4.30		
Dissipation Factor				ASTM D150
60 Hz	5.0E-3	9.0E-3		
1 MHz	0.017	0.022		
Arc Resistance	140	120	sec	ASTM D495
Comparative Tracking Index (CTI)	550	550	V	UL 746
Flammability	Dry	Conditioned	Unit	Test method
Flame Rating ⁴ (3.2 mm)	HB	--		UL 94
Optical	Dry	Conditioned	Unit	Test method
Transmittance ⁵				ASTM D1003
1070 nm : 1.60 mm	> 30	--	%	
940 nm : 1.60 mm	> 30	--	%	

Additional Information

Conditioned Conditioned to 50% RH in accordance with ISO-1110, Accelerated Method

Injection	Dry	Unit
Drying Temperature	120	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.030 to 0.060	%
Rear Temperature	304 to 318	°C
Front Temperature	316 to 329	°C
Processing (Melt) Temp	321 to 343	°C
Mold Temperature	135	°C

Amodel® A-1133 HS


polyphthalamide

Injection Notes

Storage:

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.


Isochronous Stress vs. Strain (ISO 11403-1)



Amodel® A-1133 HS

polyphthalamide


Isothermal Stress vs. Strain (ISO 11403-1)



Amodel® A-1133 HS

polyphthalamide


Secant Modulus vs. Strain (ISO 11403-1)



Amodel® A-1133 HS

polyphthalamide

Viscosity vs. Shear Rate (ISO 11403-2)



Amodel® A-1133 HS

polyphthalamide

Notes

Typical properties: these are not to be construed as specifications.

¹ Limited to use by GMNA Powertrain in water baffles, use in any other application requires approval from GM.

² 20000 hr

³ 5000 hr

⁴ These flammability ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

⁵ Transmittance for natural only.

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2020 Solvay Specialty Polymers. All rights reserved.

