TECHNYL®

TECHNYL® A 20 V25 BLACK 2006 CF

TECHNICAL DATA SHEET

Revised: January, 2019

TECHNYL® A 20 V25 Black 2006 CF is a Red Phosphorous flame retardant polyamide 66, reinforced with 25% of glass fiber, heat stabilized, for injection moulding. This grade provides robust UL 94 V-0 and a full UL yellow card while offering good mechanical properties. This grade is suitable for moulding insulating parts for electrical devices, and more generally for thin parts under stress.

GENERAL

 Commercial: Discontinued 	
 Africa & Middle East Asia Pacific	• Europe
Glass Fiber, 25% Filler by Weight	
Flame Retardant	Heat Stabilizer
Glow Wire ResistanceGWFI 960°C at 0.8 mm thickness	Low Phosphine EmissionUL 94 V0 at 0.8 mm
ConnectorsElectrical PartsElectrical/Electronic Applications	Kitchen appliancesWhite appliancesWiring & cables applications
• EC 1907/2006 (REACH)	• UL QMFZ2
RoHS Compliant	
• Black	Natural Color
Pellets	
Injection Molding	
• PA66-GF25 FR(52)	
	 Commercial: Discontinued Africa & Middle East Asia Pacific Glass Fiber, 25% Filler by Weight Flame Retardant Glow Wire Resistance GWFI 960°C at 0.8 mm thickness Connectors Electrical Parts Electrical/Electronic Applications EC 1907/2006 (REACH) RoHS Compliant Black Pellets Injection Molding PA66-GF25 FR(52)

PROPERTIES

Typical values of properties are for Natural grades				
Physical	Dry	Conditioned	Unit	Test Method
Water Absorption				ISO 62
24 hr, 23°C	0.75		%	
Equilibrium, 23°C, 50% RH	2.1		%	
Density	1.38		g/cm ³	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9400	6300	MPa	ISO 527-2/1A
Tensile Stress (Break, 23°C)	150	100	MPa	ISO 527-2/1A
Tensile Strain (Break, 23°C)	2.5	5.2	%	ISO 527-2
Flexural Modulus (23°C)	8500	5700	MPa	ISO 178
Flexural Stress (23°C)	255	170	MPa	ISO 178
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	7.0		kJ/m²	
23°C	8.0	9.0	kJ/m²	

Solvay Engineering Plastics www.solvay.com - www.technyl.com

Tel: 00 800 55 400 600 technyl-emea@solvay.com - Europe, Middle East, Africa technyl-apac@solvay.com - Asia Pacific technyl-americas@solvay.com - Americas





TECHNYL® A 20 V25 BLACK 2006 CF

Revised: January, 2019

Mechanical	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	50		kJ/m²	
23°C	55	60	kJ/m²	
Notched Izod Impact Strength (23°C)	8.0	9.0	kJ/m²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/Af
1.8 MPa, Unannealed	244		°C	
Melting Temperature	263		°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms∙cm	IEC 60093
Electric Strength (0.800 mm)	30		kV/mm	IEC 60243-1
Relative Permittivity	3.40	4.00		IEC 60250
Dissipation Factor	0.020	0.050		IEC 60250
Comparative Tracking Index (Solution A)	400		V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.8 mm	V-0			
1.6 mm	V-0			
3.2 mm	V-0			
Glow Wire Flammability Index				IEC
0.8 mm	960		°C	60695-2-12
1.6 mm	960		°C	
3.2 mm	960		°C	
Glow Wire Ignition Temperature (1.6 mm)	725		°C	IEC 60695-2-13
Oxygen Index	31		%	ISO 4589-2

PROCESSING

Injection	Dry Unit
Drying Temperature	80 °C
Suggested Max Moisture	0.20 %
Rear Temperature	265 to 275 °C
Middle Temperature	270 to 280 °C
Front Temperature	280 to 290 °C
Mold Temperature	60 to 90 °C

Solvay Engineering Plastics www.solvay.com - www.technyl.com







TECHNYL® A 20 V25 BLACK 2006 CF

Revised: January, 2019

Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

Injection Advice:

- All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Solvay recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Solvay advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% Chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
- The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design

DISCLAIMER

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANDABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.





Revised: January, 2019

SAFETY INFORMATION

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

REGULATIONS COMPLIANCE

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with ROHS Directive 2011/65/EU and 2015/863 as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

CUSTOMER SERVICES

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range on our internet product finder at the following address: http://www.technyl.com

technyl-apac@solvay.com - Asia Pacific

technyl-americas@solvay.com - Americas

technyl-emea@solvay.com - Europe, Middle East, Africa

Tel: 00 800 55 400 600



TECHNICAL DATA SHEET

TECHNYL® A 20 V25 BLACK 2006 CF

Revised: January, 2019

MULTIPOINT DATA

Isothermal Stress vs. Strain (ISO 11403-1)



Solvay Engineering Plastics www.solvay.com - www.technyl.com





TECHNYL® A 20 V25 BLACK 2006 CF

Revised: January, 2019

Notes

Typical properties: these are not to be construed as specifications.

Solvay Engineering Plastics www.solvay.com - www.technyl.com

Tel: 00 800 55 400 600 technyl-emea@solvay.com - Europe, Middle East, Africa technyl-apac@solvay.com - Asia Pacific technyl-americas@solvay.com - Americas

