

DuPont™ Crastin® SK643FR BK851

THERMOPLASTIC POLYESTER RESIN

Product Information

Crastin® SK643FR BK851 is a 20% Glass Reinforced, Flame Retardant, Polybutylene Terephthalate

Product information	Value	Unit	Test Standard
Resin Identification	PBT-GF20FR(17)	-	ISO 1043
Part Marking Code	PBT-GF20FR(17)	-	ISO 11469
Rheological properties	Value	Unit	Test Standard
Moulding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.2	%	ISO 294-4, 2577
Moulding shrinkage, parallel, annealed	0.6	%	ISO 294-4
Moulding shrinkage, normal, annealed	1.45	%	ISO 294-4
Mechanical properties	Value	Unit	Test Standard
Tensile Modulus	8300	MPa	ISO 527-1/-2
Stress at break	110	MPa	ISO 527-1/-2
Strain at break	2.8	%	ISO 527-1/-2
Flexural Strength	165	MPa	ISO 178
Charpy impact strength, 23°C	50	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	7.6	kJ/m ²	ISO 179/1eA
Thermal properties	Value	Unit	Test Standard
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	200	°C	ISO 75-1/-2
RTI, electrical			UL 746B
0.75mm	140	°C	
1.5mm	140	°C	
3mm	140	°C	
6mm	140	°C	
RTI, impact			UL 746B
0.75mm	130	°C	
1.5mm	130	°C	
3mm	130	°C	
6mm	130	°C	
RTI, strength			UL 746B
0.75mm	140	°C	
1.5mm	140	°C	
3mm	140	°C	
6mm	140	°C	
Flammability	Value	Unit	Test Standard
Burning Behav. at 1.5mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
UL recognition	yes	-	UL 94
Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
UL recognition	yes	-	UL 94
Oxygen index	32	%	ISO 4589-1/-2
FMVSS Class	DNI	-	ISO 3795 (FMVSS 302)
Electrical properties	Value	Unit	Test Standard
Comparative tracking index	225	-	IEC 60112
Other properties	Value	Unit	Test Standard
Humidity absorption, 2mm	0.13	%	Sim. to ISO 62
Water absorption, 2mm	0.32	%	Sim. to ISO 62
Density	1630	kg/m ³	ISO 1183
Injection	Value	Unit	Test Standard
Drying Recommended	yes	-	-
Drying Temperature	≥120	°C	-

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11



DuPont™ Crastin® SK643FR BK851

THERMOPLASTIC POLYESTER RESIN

Drying Time, Dehumidified Dryer	2 - 4 h	-
Processing Moisture Content	≤0.04 %	-
Melt Temperature Optimum	250 °C	-
Min. melt temperature	240 °C	-
Max. melt temperature	260 °C	-
Mold Temperature Optimum	80 °C	-
Min. mould temperature	30 °C	-
Max. mould temperature	130 °C	-
Hold pressure range	≥60 MPa	-
Hold pressure time	3 s/mm	-
Back pressure	As low as possible	-
Ejection temperature	170 °C	-

Characteristics

Regional Availability

- North America
- Europe

- Asia Pacific
- South and Central America

- Near East/Africa
- Global

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 4mm (Hytrel® measured at 2 mm), IEC Electrical properties measured at 2mm, all ASTM properties measured at 3.2mm, and test temperatures are 23 °C unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, □ or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. © 2019 DuPont de Nemours, Inc. All rights reserved.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11

