

Vydyne® ECO315 BK06

polyamide 66/6 copolymer



Vydyne ECO315 BK06 is a non-halogenated, unfilled, flame-retardant PA66/6 copolymer with excellent toughness and ductility. It is lubricated for machine feed and easy mold release

and has an Underwriters Laboratories UL 94 flammability classification of V-0 at 0.4 mm (0.016") thick.

General				
Material Status	• Commercial: Active			
Availability	• Asia Pacific	• Europe	• North America	
Additive	• Flame Retardant	• Lubricant		
Features	• Crack Resistant	• Good Mold Release	• High Elongation	
	• Ductile	• Good Toughness	• Low Density	
	• Flame Retardant	• Halogen Free	• Lubricated	
Uses	• Appliances	• Electrical Parts	• Living Hinges	
	• Automotive Electronics	• Electrical/Electronic Applications	• Printed Circuit Boards	
	• Bobbins	• Fasteners	• Switches	
	• Connectors	• Industrial Applications		
	• Electrical Housing	• Lighting Applications		
UL File Number	• E70062			
Appearance	• Black			
Forms	• Pellets			
Processing Method	• Injection Molding			

Physical	Dry	Conditioned	Unit	Test Method
Density	1.16	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.4	--	%	
Flow : 23°C, 2.00 mm	1.2	--	%	
Water Absorption				ISO 62
24 hr, 23°C	0.80	--	%	
Equilibrium, 23°C, 50% RH	2.3	--	%	

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3250	1200	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	75.0	42.0	MPa	ISO 527-2
Tensile Strain				ISO 527-2
Yield, 23°C	3.5	23	%	
Break, 23°C	22	140	%	
Flexural Modulus (23°C)	3200	1560	MPa	ISO 178
Flexural Strength (23°C)	92.0	45.0	MPa	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	5.4	--	kJ/m ²	
23°C	5.4	--	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	--		
23°C	No Break	--		
Notched Izod Impact Strength (23°C)	6.0	--	kJ/m ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	225	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	65.0	--	°C	ISO 75-2/A
Melting Temperature	244	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	1.1E-4	--	cm/cm/°C	
Transverse : 23 to 55°C, 2.00 mm	1.1E-4	--	cm/cm/°C	
RTI Elec				UL 746
0.40 mm	130	--	°C	
0.75 mm	130	--	°C	
1.5 mm	130	--	°C	
3.0 mm	130	--	°C	
RTI Imp				UL 746
0.40 mm	65.0	--	°C	
0.75 mm	65.0	--	°C	
1.5 mm	85.0	--	°C	
3.0 mm	85.0	--	°C	
RTI Str				UL 746
0.40 mm	100	--	°C	
0.75 mm	100	--	°C	
1.5 mm	100	--	°C	
3.0 mm	110	--	°C	

Vydyne® ECO315 BK06
polyamide 66/6 copolymer



Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.750 mm)	1.0E+11	--	ohms-cm	IEC 60093
Dielectric Strength (1.00 mm)	13	--	kV/mm	IEC 60243
Arc Resistance (3.00 mm)	PLC 5	--		ASTM D495
Comparative Tracking Index (3.00 mm)	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.40 mm	PLC 0	--		
0.75 mm	PLC 0	--		
1.5 mm	PLC 0	--		
3.0 mm	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 1	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.40 mm	PLC 4	--		
0.75 mm	PLC 4	--		
1.5 mm	PLC 4	--		
3.0 mm	PLC 3	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.40 mm	V-0	--		
0.75 mm	V-0	--		
1.5 mm	V-0	--		
3.0 mm	V-0	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.40 mm	960	--	°C	
0.75 mm	960	--	°C	
1.5 mm	960	--	°C	
3.0 mm	960	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.40 mm	875	--	°C	
0.75 mm	875	--	°C	
1.5 mm	775	--	°C	
3.0 mm	725	--	°C	
Oxygen Index	29	--	%	ISO 4589-2

Injection	Dry Unit
Drying Temperature	80 °C
Drying Time	4.0 hr
Suggested Max Regrind	50 %
Rear Temperature	240 to 270 °C
Middle Temperature	240 to 270 °C
Front Temperature	240 to 270 °C
Nozzle Temperature	240 to 270 °C
Processing (Melt) Temp	250 to 270 °C
Mold Temperature	65 to 95 °C

Notes

Typical properties: these are not to be construed as specifications.

¹ Typical properties: these are not to be construed as specifications.



North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 6340 3300

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.