

Amodel® A-1130 FW

polyphthalamide

Amodel® A-1130 FW is a 30% glass-fiber reinforced polyphthalamide (PPA) grade containing a solid lubricant. This resin was designed for moderate-pressure, low-velocity friction and wear applications.

- Black: A-1130 FW BK 324

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight	
Additive	• PTFE Lubricant	
Features	• Chemical Resistant • Creep Resistant • Good Dimensional Stability • Good Stiffness	• High Strength • Low Friction • Wear Resistant
Uses	• Bearings • Bushings	• Filters • Gears
RoHS Compliance	• RoHS Compliant	
Automotive Specifications	• ASTM D6779 PA1270G30	• ISO 1874-PA6T/6I/66, MH, 11-110, GF30
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Typical Value	Unit	Test method
Density	1.55	g/cm ³	ISO 1183/A

Mechanical	Typical Value	Unit	Test method
Tensile Modulus	11200	MPa	ISO 527-2
Tensile Stress (Break)	187	MPa	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Modulus	9580	MPa	ISO 178
Flexural Stress	252	MPa	ISO 178

Thermal	Typical Value	Unit	Test method
Heat Deflection Temperature 1.8 MPa, Unannealed	285	°C	ISO 75-2/A
Melting Temperature	313	°C	ISO 11357-3

Injection	Typical Value	Unit
Drying Temperature	110	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.030 to 0.060	%
Rear Temperature	304 to 318	°C

Amodel® A-1130 FW

polyphthalamide

Injection	Typical Value	Unit
Front Temperature	316 to 329	°C
Processing (Melt) Temp	329 to 343	°C
Mold Temperature	135	°C

Injection Notes

Storage:

- Amodel® PPA compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® PPA resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® PPA processing guide.

Notes

Typical properties: these are not to be construed as specifications.

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2020 Solvay Specialty Polymers. All rights reserved.

