

Vydyne® R220

polyamide 66



Vydyne R220 is a 40% mineral-reinforced PA66 resin formulated for improved impact strength. Available in natural, it is an injection-molding grade formulated to retain the inherent processing advantages of unreinforced PA66 while enhancing rigidity, strength and heat resistance. Vydyne R220 maintains the chemical resistance typical of PA66 to a wide variety of chemicals, gasoline, oils, greases and solvents.

Vydyne R220 resin utilizes a unique mineral-reinforced PA66 system developed by Ascend Performance Materials to satisfy the market need for a high-rigidity thermoplastic as an alternative to certain metals. This mineral system provides two key features:

- (1) isotropic behavior-property development in molded parts is usually independent of flow direction.
- (2) a reduction in the tendency to develop sink marks in heavy cross sections such as molded-in bosses and ribs.

While not sink-free, parts made from Vydyne R220 can often permit boss and rib design or wall cross section changes that

would not be tolerable in other unreinforced thermoplastic materials. Thus Vydyne R220 resin offers more uniform molded part strength and performance, as well as wider latitude in part design.

Vydyne R220 resin is a workhorse of Ascend Performance Materials' full line of mineral-reinforced PA66 resins, providing the best overall balance of properties. Vydyne R220 is heat stabilized and designed to provide increased ductility and reduced melt viscosity vs. unreinforced materials. This ductility improvement results in tougher, more impact-resistant molded parts. The reduction in melt viscosity enhances overall ease of injection-molding, resulting in minor reductions in tensile strength, modulus and heat distortion temperature. Parts manufactured from Vydyne R220 have successfully withstood paint bake oven cycles without significant loss of either dimensional stability or part properties.

General	
Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> Asia Pacific Europe North America
Filler / Reinforcement	<ul style="list-style-type: none"> Mineral, 40% Filler by Weight
Additive	<ul style="list-style-type: none"> Heat Stabilizer
Features	<ul style="list-style-type: none"> Chemical Resistant Ductile Gasoline Resistant Good Impact Resistance Good Strength Good Toughness Grease Resistant Heat Stabilized High Heat Resistance High Rigidity Oil Resistant Solvent Resistant
Uses	<ul style="list-style-type: none"> Automotive Exterior Parts Automotive Under the Hood Cams Gears Housings Industrial Applications Power/Other Tools
Agency Ratings	<ul style="list-style-type: none"> ASTM D4066 PA114M40 ASTM D6779 PA084M40
Automotive Specifications	<ul style="list-style-type: none"> CHRYSLER MS-DB-41 CPN 2310 CHRYSLER MS-DB-41 CPN 3189 DELPHI SD-2-214 Sec. 4.1 FORD ESB-M4D353-A4 GM GMP.PA66.007
UL File Number	<ul style="list-style-type: none"> E70062
Appearance	<ul style="list-style-type: none"> Natural Color
Forms	<ul style="list-style-type: none"> Pellets
Processing Method	<ul style="list-style-type: none"> Injection Molding

Physical	Dry	Conditioned	Unit	Test Method
Density	1.48	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.0	--	%	
Flow : 23°C, 2.00 mm	1.1	--	%	
Water Absorption				ISO 62
24 hr, 23°C	1.1	--	%	
Equilibrium, 23°C, 50% RH	1.6	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	6900	2600	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	103	73.0	MPa	ISO 527-2
Tensile Strain				ISO 527-2
Yield, 23°C	1.5	16	%	
Break, 23°C	6.0	30	%	
Flexural Modulus (23°C)	6100	2300	MPa	ISO 178
Flexural Stress (23°C)	124	50.0	MPa	ISO 178
Poisson's Ratio	0.40	--		ISO 527
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-30°C	6.0	8.0	kJ/m ²	
23°C	7.0	17	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179
-30°C	110	130	kJ/m ²	
23°C	140 kJ/m ²	No Break		
Notched Izod Impact Strength				ISO 180
-30°C	7.0	7.0	kJ/m ²	
23°C	9.0	16	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	222	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	118	--	°C	ISO 75-2/A
Melting Temperature	258	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	6.3E-4	--	cm/cm/°C	
Transverse : 23 to 55°C, 2.00 mm	6.0E-4	--	cm/cm/°C	
Additional Information	Dry	Conditioned	Unit	Test Method
Automotive Materials - (thickness d = 1mm)	+	--		FMVSS 302

Injection	Dry Unit
Drying Temperature	80 °C
Drying Time	4.0 hr
Suggested Max Regrind	25 %
Rear Temperature	280 to 310 °C
Middle Temperature	280 to 310 °C
Front Temperature	280 to 310 °C
Nozzle Temperature	280 to 310 °C
Processing (Melt) Temp	285 to 305 °C
Mold Temperature	65 to 95 °C

Notes

Typical properties: these are not to be construed as specifications.

¹ Typical properties: these are not to be construed as specifications.



North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 6340 3300

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.